



OPT.AWPCLEAR-500A

2K High Gloss Lacquer

2K High Gloss Lacquer is a 2K superior high gloss crystal clear finish that has excellent gloss retention. This product is easy to activate and apply with mechanical polishing possible after 24 hours.

Suitable substrates

Solvent or water based basecoat paint

- Genuine 2K isocyanate lacquer
- Brilliant gloss retention
- Very scratch resistant
- Gives a spray gun finish every time

Technical Data

Chemical base	Acrylic Resin
VOC content	138 g/200ml
Coverage	0.30 - 0.40m ²
Storage notes	3 years in appropriate storage (-10°-25°C, relative air humidity of max. 60%)

Environmentally sound

The products supplied by Optima are 100% free of heavy metals and the caps and packaging are made of recyclable material.

Disposal

Completely emptied cans should be put in recycling skips or appropriate container. Cans which are not empty should be disposed off as special refuse.

Additional information

This application and technical information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by us are suitable for your special application. The use and processing is beyond our control and therefore exclusively is the responsibility of the user.






optima

OPT.AWPCLEAR-500A

2K High Gloss Lacquer

Application Data



2-3 coats
@ 50µm



Dust dry
5 minutes @ 20°C
Touch dry
5 hours
Overcoatable
2 minutes @ 20°C



15-20 minutes



UV 15-20 minutes
20°C 24 hours
40°C 40 minutes



Protections:
Air fed respiration
equipment




Protective gloves,
e.g. from latex or
nitrile

Application Method




Remove cap off the bottom of the can. Remove the ring and feed through the hole in the bolt.




Pull the bolt in the bottom of the can with the aid of the metal ring far as it will go.




By twisting 360°, the activator will be completely released.



Before use, shake the aerosol for 2 minutes and spray a sample area.



Apply in cross coats from a distance of 250mm from object.



After use turn aerosol upside down, press the nozzle for approx. 5 sec and clear valve.

