



## Optima Masking Tape Technical Data Sheet

### DESCRIPTION

Masking tape for automotive body shops.

### PRODUCT DATA

#### Backing

58 g/m<sup>2</sup> natural saturated crepe paper; white.

#### Adhesive

Dry natural rubber and resins solvent based.

	Unit	Value	Method
<b>Total thickness</b>	mm	0.130	PSTC 133
<b>Adhesion to steel</b>	N/25mm	4.5	PSTC 101
<b>Tensile strength MD</b>	N/25mm	85	PSTC 131
<b>Elongation at break</b>	%	8.5	PSTC 131
<b>Temp. Resistance</b>	°C	80°C (100°C x 30min)	=

### APPLICATION

Masking tape suitable for high performance application for use in automotive repair workshops.

Features	Benefits
Dry natural rubber and resins solvent based adhesive	<ul style="list-style-type: none"> <li>• Easy removal without adhesive residue</li> <li>• Excellent resistance to paint and lacquer thinners</li> <li>• Good adhesion even on irregular surfaces</li> <li>• Heat resistant up to 100°C (30 min)</li> </ul>
Saturated paper backing	<ul style="list-style-type: none"> <li>• Well conformable to most surfaces</li> <li>• Compatible with most common paints and lacquers</li> <li>• Removable without breaking</li> <li>• Hand tearable</li> </ul>

### CONDITIONS OF USE AND CONFORMITY

Product shelf life and storage: 12 months; suggested storage temperature shall range from 15°C to 25°C with max. relative humidity of 65%. Material shall be stored away from heat sources and possibly kept in original package, avoiding light exposure as well. When temperature are lower than suggested, it is always required to precondition the tape at normal temperature before use. This information is given to the best of LKQ Coatings knowledge. Values are typical and do not constitute a specification. Customers are required to do their own testing under their working condition for their intended application. Any liability arising in respect of our products will be limited to the value of those products charged to the customer excluding any consequential loss.

**Optima Products**, Newberry House, Michigan Drive, Tongwell,  
Milton Keynes, Buckinghamshire, MK15 8HQ  
Tel: 01908 611117 Email: [Optimaproducts@LKQCoatings.com](mailto:Optimaproducts@LKQCoatings.com)

